



Test Report No. 68.401.26.1889.01B
Rev. 00
Dated 2026-06-04

Applicant: YANGJIANG YANGDONG YASHION INDUSTRIAL AND TRADING CO., LTD

Address: No.56, Taoran Road, Dongcheng Town, Yangdong, Yangjiang, Guangdong, China

Sample Description: Rubber wood cutting board

Model No.: 8054796270170

Supplier: YANGJIANG YANGDONG YASHION INDUSTRIAL AND TRADING CO.,LTD

Buyer: Seedlift di C.P.

Sample Received Date: 2026-05-18

Test Period: From 2026-05-18 to 2026-05-27

Location of Testing: TÜV SÜD Certification and Testing (China) Co., Ltd. Shenzhen Branch

Purpose of examination: As specified by client, to test as regulated by the German Food & Feed Acts LFGB (§ 30 & 31) and Regulation (EC) No.1935/2004.

Test Result: Refer to following page(s)

Remark:
- The result relates only to the items tested.
- The testing approach, the testing methods, and the reported results in this report demonstrate compliance or non-compliance to the client's requirements which were mutually agreed at the contract review and stipulated in the quotation. The testing approach, the testing methods, and the reported results may not or only partially fulfil the associated requirements of the applicable regulations.

TÜV SÜD Certification and Testing (China) Co., Ltd. Shenzhen Branch
TÜV SÜD Group

Prepared by:

Sophie Fu
Project Handler



Reviewed by:

Scarlett Liang
Designated Reviewer

Any use for advertising purposes must be granted in writing. This test report may only be quoted in full. This report is the result of a single examination of the object in question. It does not imply a general statement regarding the quality of products from regular production. For further details please see Testing, Certification, Validation and Verification Regulations, chapter A-3.3.
Disclaimer Measurement Uncertainty: Unless otherwise agreed upon, pass or fail verdicts are given based on the measured values without consideration of measurement uncertainties. Please note, every test method has a measurement uncertainty which has been evaluated by the laboratory according to ISO IEC 17025 requirements. By taking measurement uncertainties into account it might happen that measured values can neither be assessed as pass or fail.

TÜV SÜD Certification and Testing (China) Co., Ltd. Shenzhen Branch
TÜV SÜD Group
Building 12 & 13, Zhiheng Wisdomland Business Park,
Guankou Erlu, Nantou, Nanshan District,
Shenzhen, Guangdong 518052 China

Tel.: (86) 755 88286998
Fax: (86) 755 88285299



Test Report No. 68.401.26.1889.01B
Rev. 00
Dated 2026-06-04

SUMMARY OF TEST RESULTS

Test Requested	Conclusion	Remarks
For material: Wood, Bamboo Test for compliance with French Notice Information n° 2012-93. 1. Specific Migration of Formaldehyde 2. Pentachlorophenol Content 3. Extractable Lead, Cadmium, Mercury	PASS	
Sensory test 4. Sensory test with reference to DIN 10955: 2024	PASS	



1. TESTED SUBJECT DESCRIPTION

Test No.	Sample No.	Tested Material Description	Photo
T1	001	Primary wood cutting board	



2. TEST RESULT

2.1. SPECIFIC MIGRATION OF FORMALDEHYDE TEST FOR WOOD, BAMBOO

Test method: With reference to EN 13130-1: 2004, the sample(s) were migrated with food simulant, followed by Ultraviolet-visible Spectrophotometer (UV-Vis) analysis.

Testing condition and simulant: 3% acetic acid at 70 °C for 2 hour(s).

Test Item	CAS No.	Result [mg/kg]	Requirement [mg/kg]
		Sample 001	
Migration of Formaldehyde	50-00-0	< 3	≤ 15

Note:

- “mg/kg” denotes milligram per kilogram foodstuff
- The specification was quoted from French Notice Information n° 2012-93.

2.2. PENTACHLOROPHENOL (PCP) CONTENT TEST FOR WOOD, BAMBOO

Test method: Solvent extraction with acetone, followed by Gas Chromatography and Mass Spectrometry (GC-MS) analysis.

Test Item	CAS No.	Result [mg/kg]	Requirement [mg/kg]
		Sample 001	
Pentachlorophenol (PCP)	87-86-5	< 0.05	≤ 0.1

Note:

- “mg/kg” denotes milligram per kilogram.
- The specification was quoted from French Notice Information n° 2012-93.

2.3. EXTRACTABLE LEAD, CADMIUM, MERCURY TEST FOR WOOD, BAMBOO

Test method: With reference to EN 645: 1994/EN 647: 1994, EN 12497: 2005 and EN 12498: 2018, the sample(s) were migrated with food simulant, followed by Inductively Coupled Plasma Mass Spectrometry (ICP-MS) analysis.

Testing condition and simulant: Distilled water at 23 °C for 24 hour(s) .

Test Item	Result [mg/kg]	Requirement [mg/kg]
	Sample 001	
Extractable Lead (Pb)	< 0.1	≤ 3
Extractable Cadmium (Cd)	< 0.1	≤ 0.5
Extractable Mercury (Hg)	< 0.1	≤ 0.3

Note:

- “mg/kg” denotes milligram per kilogram.
- The specification was quoted from French Notice Information n° 2012-93.

2.4. SENSORY TEST

Test method: With reference to DIN 10955: 2024. The submitted sample was treated with food stimulant. After this treatment, examined by 6 panels judges with regard to any divergence in smell and taste.

Testing condition and simulant: Cucumber at 40°C for 0.5 hour(s) .

Test Item	Grading Result	Recommended Level
	Sample 001	
Transfer of Smell	1	< 2
Transfer of Taste	1	< 2

Note:

- Explanation for grading are listed as below:
Grading 0: No perceptible taste/smell deviation
Grading 1: Just perceptible taste/smell deviation
Grading 2: Weak taste/smell deviation
Grading 3: Clear taste/smell deviation
Grading 4: Strong taste/smell deviation

-----End of Report-----